

Packing for *INDION*® Resins

| Moist Resins | | Dry Resins | |
|-------------------------------|--------------------------|---|-----------------|
| HDPE liner bags | 25 / 50 lts | Dry Beads | |
| LDPE liner bags | 0.5 cft / 1 cft / 25 lts | HDPE carboys with inner double plastic liner bags | 25 / 50 kgs |
| Super sack | 1000 lts / 35 cft | | |
| MS drums with liner bags | 180 lts | | |
| Fibre drums with liner bags | 7 cft | Dry Powders | |
| PVC jars with liner bags | 5 / 6 lts | HDPE carboys with inner double plastic liner bags | 6 / 20 / 40 kgs |
| HDPE drums with liner bags | 50 / 100 / 180 lts | | |
| Vacuum packing with LDPE bags | 1 cft / 25 lts | | |

Protection of Ion Exchange Resins during Storage

Ion exchange resins, supplied in dry or moist condition, require proper care at all times. Always keep the resins drums / bags closed and in shade at a temperature between 10°C and 40°C.

Moist Resins: Resins which are supplied in moist condition should not be allowed to dry. Regularly open the drums / bags and check the condition of the resins. If the resin is not moist enough, add demineralised water to keep it in completely moist condition.

Dry Resins: Resins which are supplied as dry beads or dry powders should not be allowed to come in contact with moisture.

Measurement

Moist Resins: All water treatment resins and resins supplied in moist condition are generally sold on volume basis. The volume is measured in a column after backwashing, settling and draining of water to the bed surface.

Dry Resins: All dry resins are sold on weight basis.

Warning

Strong oxidising agents such as nitric acid, degrade ion exchange resins to a considerable extent. This may result in an explosive reaction. Thus, before using strong oxidising agents, consult sources knowledgeable in handling of such material.

Our state-of-the-art manufacturing facilities are ISO 9001, ISO 14001 & ISO 45001 certified

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice. Please contact our regional / branch offices for current product specifications.

INDION is the registered trademark of Ion Exchange (India) Ltd.



The Preferred Choice

Our INDION range is backed by sustained focus on customer needs, intensive product and application R&D, sound technical support and wide application knowhow. Add to this **continuous innovation, worldclass quality**, state-of-the-art ISO 9001 & 14001 certified facilities, an **FDA approved** pharmaceutical grade resin manufacturing unit...and you get the perfect recipe that makes INDION the preferred choice across sectors for over five decades.

Wide Range. Extensive Applications.

A complete range of cation & anion resins for water and waste water treatment as well as a host of speciality applications - pharmaceutical excipients, catalysts, nuclear grade resins, chelating resins for brine softening and heavy metal removal, adsorbent grade resins, resins for removal of colour, odour, organics, nitrate & tannin, resins for purification of bio-diesel, sugar, food & beverages and many more...

- Refinery & Petrochemical
- Steel, Power & Paper
- Food & Beverages
- Pharmaceuticals
Bio-technology & Electronics
- Textiles, Sugar, Auto & Mini-steel
- Cement & Chemicals



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices

Bengaluru | Bhubaneswar | Chandigarh | Chennai
Delhi | Hyderabad | Kolkata | Lucknow | Vadodara
Vashi | Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices

Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Portugal | Saudi Arabia | Singapore
South Africa | Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada
Overseas - Bangladesh | Indonesia | Saudi Arabia | UAE

All India Service and Dealer Network

www.ionexchangeglobal.com | www.ionresins.com



INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications | |
|---|--------------------|---------------------|-------------------------|--|------------------------------|------------------------------|----------------------------------|--------------------------------|------------------------|---|--|
| Industrial Water Treatment | | | | | | | | | | | |
| INDION Controlled Particle Size Ion Exchange Resins (CPS Resins) | | | | | | | | | | | |
| Anion Exchange Resin | | | | | | | | | | | |
| SBA | Gel | GS 3000 (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.50 – 0.65 (effective size) | 48 – 58 | 60 (OH ⁻) | 1.3 | Cl ⁻ to OH ⁻ 25 – 30 | Demineralisation in co-current and countercurrent mode. Condensate polishing & caprolactum purification. |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Gel | 2250 Na | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.50 – 0.65 (effective size) | 43 – 50 | 120 | 2.0 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for water softening. |
| | | 2250 H | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.50 – 0.65 (effective size) | 49 – 55 | 120 | 1.8 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for demineralisation. |
| Industrial Water Treatment | | | | | | | | | | | |
| Anion Exchange Resins | | | | | | | | | | | |
| SBA | Isoporous | FF-IP (Type 1) | Crosslinked Polystyrene | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 47 – 55 | 60 (OH ⁻) | 1.2 | Cl ⁻ to OH ⁻ 10 – 15 | Demineralisation in co-current and countercurrent mode. |
| | | FF-IP (MB) | Crosslinked Polystyrene | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 47 – 55 | 60 (OH ⁻) | 1.2 | Cl ⁻ to OH ⁻ 10 – 15 | Used in mixed bed. |
| | | N-IP (Type 2) | Crosslinked Polystyrene | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 45 – 53 | 40 (OH ⁻) | 1.2 | Cl ⁻ to OH ⁻ 10 – 15 | Demineralisation in co-current and countercurrent mode. |
| | Gel | GS 300 (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 48 – 58 | 60 (OH ⁻) | 1.3 | Cl ⁻ to OH ⁻ 25 – 30 | Demineralisation in co-current and countercurrent mode. condensate polishing & caprolactum purification. |
| | | GS 300 (OH) | Styrene DVB | -N ⁺ R ₃ | OH ⁻ | 0.3 – 1.2 | 60 – 70 | 60 (OH) | 1.0 | Cl ⁻ to OH ⁻ 25 – 30 | Premium grade anion exchange resin used for demineralisation in regenerable mixed bed application. |
| | | GS 400 (Type 2) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 45 – 51 | 40 (OH ⁻) | 1.2 | Cl ⁻ to OH ⁻ 10 – 15 | Demineralisation in co-current and countercurrent mode. |
| | Macroporous | 810 (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 56 – 63 | 60 (OH ⁻) | 1.0 | Cl ⁻ to OH ⁻ 15 – 20 | Demineralisation in co-current and countercurrent mode. |
| | | 810 HC (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 47 – 55 | 60 (OH) | 1.2 | Cl ⁻ to OH ⁻ 10 – 20 | Premium grade anion exchange resin for demineralisation in co-current and countercurrent mode. |
| | | 810 SO ₄ | Crosslinked polystyrene | -N R ₄ ⁺ | SO ₄ ⁻ | 0.45 – 0.6 (effective size) | 56 – 63 | 60 (OH ⁻) | 1.0 (Cl ⁻) | Cl ⁻ to OH ⁻ 15 – 20 | Used in condensate polishing unit. |
| | | 830 (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 57 – 66 | 80 (Cl ⁻) | 0.95 | Cl ⁻ to OH ⁻ 7 – 17 | Removal of organics & colour from water. |
| | | 820 (Type 2) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 54 – 61 | 40 (OH ⁻) | 1.0 | Cl ⁻ to OH ⁻ 10 – 15 | Demineralisation in co-current and countercurrent mode. |
| | | 820 HC (Type 2) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 46 – 53 | 40 (OH) | 1.2 | Cl ⁻ to OH ⁻ 10 – 20 | Premium grade anion exchange resin for demineralisation in co-current and countercurrent mode. |
| WBA | Macroporous | 850 | Styrene DVB | -NR ₂ -N ⁺ R ₃ | Free base | 0.3 – 1.2 | 47 – 55 (Cl ⁻) | 60 | 1.5 | FB to hydrochloride 25 max | Removal of strong acids from water. |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Gel | 220 Na | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 50 – 55 | 140 | 1.8 | Na ⁺ to H ⁺ 8 approx. | Standard grade cation exchange resin for water softening. |
| | | 222 Na | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 47 – 53 | 120 | 1.92 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for water softening. |
| | | 223 H | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 49 – 55 | 120 | 1.9 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for demineralisation in regenerable mixed bed application. |
| | | 225 H | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 49 – 55 | 120 | 1.8 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for demineralisation. |

*meq/dry g

SAC: Strong Acid Cation, SBA: Strong Base Anion, WBA: Weak Base Anion, WAC: Weak Acid Cation, SPL: Speciality

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications | |
|-----------------------------------|--------------------|---------------------|-------------------------------|---|-----------------------------------|-----------------------------|----------------------------------|--------------------------------|------------------------|--|---|
| Industrial Water Treatment | | | | | | | | | | | |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Gel | 225 Na | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 43 – 50 | 120 | 2.0 | Na ⁺ to H ⁺ 8 approx. | Premium grade cation exchange resin for water softening. |
| | | 525 H | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 44 – 49 | 120 | 1.95 | Na ⁺ to H ⁺ 6 approx. | Special grade cation exchanger for use in layered bed and for mixed bed condensate polishing. |
| | | 525 Na | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 38 – 44 | 130 | 2.15 | Na ⁺ to H ⁺ 6 approx. | Premium grade cation exchange resin for water softening. |
| | | 225 Na F | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 43 – 50 | 140 | 2.0 | Na ⁺ to H ⁺ 8 approx. | In the treatment of foodstuffs, beverages, potable water and water used in the processing of food. This product conforms to NSF / ANSI / CAN 61, NSF / ANSI 372 & is certified with GOLD SEAL from WQA. |
| | | 222 Na F | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 47 – 53 | 120 | 1.92 | Na ⁺ to H ⁺ 8 approx. | In the treatment of foodstuffs, beverages, potable water and water used in the processing of food. This product conforms to NSF / ANSI / CAN 61, NSF / ANSI 44 & is certified with GOLD SEAL from WQA. |
| | | 222 Na BL | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 46 – 51 | 140 | 1.9 | Na ⁺ to H ⁺ 8 approx. | Solvent free cation – in the treatment of foodstuffs, beverages, potable water and water used in the processing of food. |
| | | 303 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 49 – 55 | 120 | 2.0 (Na ⁺) | Na ⁺ to H ⁺ 8 approx | Colour indicating resin. Colour changes at the time of exhaustion. |
| | Macroporous-SPL | 730 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 54 – 57 | 120 | 1.7 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Recovery of metals from aqueous and non-aqueous streams. |
| | | 790 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 51 – 55 | 120 | 1.9 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Demineralisation in co-current, countercurrent mode and condensate water treatment. |
| | | 790 C | Crosslinked polystyrene | -SO ₃ ⁻ | H ⁺ | 0.45 – 0.6 (effective size) | 51 – 55 | 120 | 1.7 | Na to H 6 | Used in condensate polishing unit. |
| WAC | Gel | 236 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | 0.3 – 1.2 | 46 – 54 | 120 | 4.0 | H ⁺ to Na ⁺ 80 – 120 | Removal of alkaline hardness from water. |
| | Macroporous | 662 | Methacrylic DVB | -COO ⁻ | H ⁺ | 0.3 – 1.2 | 44 – 50 | 100 | 3.8 | H ⁺ to Na ⁺ 70 max | Removal of alkaline hardness from water. |
| Mixed Bed Resins | | | | | | | | | | | |
| | | MB 6SR/ Refill Pack | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | Super-regenerated mixture of cation and anion for producing ultrapure water. |
| | | MB – 11 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | 1:1 volume ratio of cation in H ⁺ and anion in OH ⁻ to produce high purity demineralised water. |
| | | MB – 11 GMB | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | Non-regenerable mixed bed application where highest quality water is required. Colour changes at the time of exhaustion. |
| | | MB – 12 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | 1:2 stoichiometrically equivalent volume ratio of cation in H ⁺ and anion in OH ⁻ to produce high purity demineralised water. |
| | | MB – 115 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | 40:60 volume ratio of cation and anion to produce high purity demineralised water. |
| | | MB 151 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | Non-regenerable EDM application. |
| | | MB 1150 HP | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.5 – 0.65 (effective size) | - | 60 | - | - | Production of high purity water in electronic & pharma industry. |
| Oil Removal Resin | | | | | | | | | | | |
| SPL | Oleophilic Resin | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 35 – 41 | 120 | 1.6 to 1.7 | - | Oil removal from steam condensate of petroleum refineries, petroleum products & water contaminated with hydrocarbon. | |

*meq/dry g

SAC: Strong Acid Cation, SBA: Strong Base Anion, WBA: Weak Base Anion, WAC: Weak Acid Cation, SPL: Speciality

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications | |
|--------------------------------|--------------------|---|--------------------------------|--------------------------------|------------------|-----------------------------|----------------------------------|--------------------------------|-----------------------|---|--|
| Potable Water Treatment | | | | | | | | | | | |
| Polyiodide Resin | | | | | | | | | | | |
| SPL | SRCD I | Crosslinked Polymer impregnated with iodine | -N ⁺ R ₃ | I ₃ ⁻ | 0.3 – 1.2 | - | 15 – 35 | - | - | Disinfection of potable water. | |
| Arsenic and Iron Removal Resin | | | | | | | | | | | |
| SPL | ASM | Crosslinked Polystyrene | - | - | 0.3 – 1.2 | 47 – 54 | 60 | 0.5 - 2.0 g As/l | - | Removal of Arsenic from potable water. This product conforms to NSF / ANSI / CAN 61 & is certified with GOLD SEAL from WQA. | |
| | ISR | Crosslinked Polystyrene | - | - | 0.3 – 1.2 | 45 – 55 | 45 | - | - | Removal of dissolved Iron from water. This product conforms to NSF / ANSI / CAN 61 & is certified with GOLD SEAL from WQA. | |
| Fluoride Removal Resin | | | | | | | | | | | |
| SPL | RS-F | Styrene DVB | NA | - | 0.3 – 1.2 | 50 – 60 | 60 | - | - | Removal of fluoride from water. | |
| Perchlorate Removal Resin | | | | | | | | | | | |
| SPL | PCR | Crosslinked Polystyrene | -NR ₄ ⁺ | Cl ⁻ | 0.3 – 1.2 | 35 – 45 | 90 (Cl ⁻) | 0.8 | - | Selective removal of perchlorate from ground water. | |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Gel | 225 Na F | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 43 – 50 | 140 | 2.0 | Na ⁺ to H ⁺ 8 approx. | High purity food grade resin for treatment of potable water and food stuff. This product conforms to NSF / ANSI / CAN 61, NSF / ANSI 372 & is certified with GOLD SEAL from WQA. |
| | | 2250 Na F | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | 0.5 – 0.65 (effective size) | 43 – 50 | 140 | 2.0 | Na ⁺ to H ⁺ 8 approx. | High purity CPS food grade resin for treatment of potable water & food stuff. |
| | | 222 Na NS | Crosslinked Polystyrene | -SO ₃ ⁻ | Na ⁺ | 0.3 – 1.2 | 43 – 49 | 120 | 1.9 | Na ⁺ to H ⁺ 8 approx. | Water softening application. This product conforms to NSF / ANSI / CAN 61 & is certified with GOLD SEAL from WQA. The product is manufactured by a non solvent process. |
| WAC | Microporous | 266 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | 0.3 – 1.2 | 46 – 54 | 120 | 4.2 | H ⁺ to Na ⁺ 65 max | Removal of alkaline hardness from water. |
| Anion Exchange Resin | | | | | | | | | | | |
| SBA | Macroporous | NSSR (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 45 – 55 | 100 (Cl ⁻) | 0.9 | Cl ⁻ to NO ₃ ⁻ Negligible | Selective removal of Nitrates from water. This product conforms to NSF / ANSI / CAN 61 & is certified with GOLD SEAL from WQA. |
| Oxidation, Reduction Catalyst | | | | | | | | | | | |
| SPL | ORC | - | - | - | 0.3 – 1.2 | - | - | - | - | Removal of halogens and oxidising agents. | |
| Nuclear Grade Resins | | | | | | | | | | | |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Gel | 223 H NG | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 49– 55 | 120 | 1.9 | - | High purity ion exchange resin (in hydrogen form) for use in nuclear power plants. |
| | | 2230 H NG | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.5 – 0.65 (effective size) | 49 – 55 | 120 | 1.9 | - | High purity CPS ion exchange resin (in hydrogen form) for use in nuclear power plants. |
| | | 223 Li | Styrene DVB | -SO ₃ ⁻ | Li ⁺ | 0.3 – 1.2 | 47 – 53 | 120 | 1.9 | - | High purity ion exchange resin (in lithium form) for use in nuclear power plants. |
| Anion Exchange Resins | | | | | | | | | | | |
| SBA | Gel | ARU 104 | Crosslinked Polystyrene | N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 38 – 42 | 80 | 1.6 | - | Recovery of Uranium from leach liquors. |
| | | GS 300 NG | Styrene DVB | -N ⁺ R ₃ | OH ⁻ | 0.3 – 1.2 | 60 max | 60 | 1.1 | - | High strength strong base anion resin (Type I) for use in nuclear power plants. |

* meq/dry g

SAC: Strong Acid Cation, SBA: Strong Base Anion, WBA: Weak Base Anion, WAC: Weak Acid Cation, SPL: Speciality

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications | |
|-------------------------------|--------------------|-------------|-------------------------|---|------------------------------------|-----------------------------|----------------------------------|--------------------------------|------------------------|---|---|
| Nuclear Grade Resins | | | | | | | | | | | |
| Anion Exchange Resins | | | | | | | | | | | |
| SBA | Gel | GS 3000 NG | Styrene DVB | -N ⁺ R ₃ | OH ⁻ | 0.5 – 0.65 (effective size) | 60 max | 60 | 1.1 | - | High strength CPS strong base anion resin (Type I) for use in nuclear power plants. |
| | | GS 80 | Crosslinked Polystyrene | -N ⁺ R ₃ | -SO ₃ ⁻ | 0.3 – 1.2 | 47 – 55 | - | 0.8 | - | Oxygen scavenging. |
| Mixed Bed Resins | | | | | | | | | | | |
| | Mixed Resins | CAM – 14 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | 1:4 volume mixture of cation and anion to produce high purity alkaline water for use in nuclear power plants. |
| | | CAM – 19 | Styrene DVB | -SO ₃ ⁻ -N ⁺ R ₃ | Li ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | 1:9 volume mixture of cation and anion. Used in nuclear power plants. |
| Catalyst Grade Resins | | | | | | | | | | | |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Macroporous | 140 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.42 – 1.2 | <3 | 150 | 4.8* | - | Catalyst for organic reactions like esterification etc. |
| | | 130 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.42 – 1.2 | <3 | 150 | 4.8* | - | Catalyst grade resin for esterification and alkylation reactions. |
| | | 190 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.42 – 1.2 | <3 | 150 | 4.7* | - | Premium catalyst for specialised applications such as esterification, alkylation etc. |
| | Gel | 770 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 63 – 66 | 120 | 1.4 | - | Catalyst for manufacture of butyl acetate, ethylacetate, olefin hydration & bisphenol A. |
| Anion Exchange Resin | | | | | | | | | | | |
| WBA | Macroporous | 860 | Styrene DVB | -NR ₂ -N ⁺ R ₃ | Free base | 0.3 – 1.2 | 52 – 56 (Cl ⁻) | 60 | 1.4 | FB to hydrochloride 25 max | As catalyst in aldolization reactions. |
| Hydrometallurgy | | | | | | | | | | | |
| Chelating Resins | | | | | | | | | | | |
| | | MSR | Styrene DVB | Thiol | H ⁺ | 0.3 – 1.2 | 38 – 43 | 60 | 3.6* | - | Selective adsorption of bivalent mercury from industrial effluents. |
| | | TCR | Styrene DVB | Thio-Uronium | - | 0.3 – 1.2 | 41 – 47 | 80 | 1.4 | - | Selective recovery of mercury and precious metals. |
| | | BSR | Styrene DVB | Amino Phosphonic | Na ⁺ | 0.42 – 1.2 | 60 – 70 | 80 | 2.0 (H ⁺) | H ⁺ to Na ⁺ <45 H ⁺ to Ca ⁺⁺ <20 | Decalcification of secondary brine in chloralkali industry. |
| | | SIR | Styrene DVB | Iminodiacetic | Na ⁺ | 0.3 – 1.2 | 52 – 58 | 90 | 2.2 (H ⁺) | - | Extraction and recovery of metals, removal of heavy metals from various organic or inorganic chemical products. |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Macroporous | 790 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 51 – 55 | 120 | 1.9 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Recovery of metals from aqueous and non-aqueous streams. |
| | | 730 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 54 – 57 | 120 | 1.7 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Recovery of metals from aqueous and non-aqueous streams. |
| | | 740 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 64 – 68 | 120 | 1.3 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Recovery of metals from aqueous and non-aqueous streams. |
| WAC | Gel | 236 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | 0.3 – 1.2 | 46 – 54 | 120 | 4.0 | H ⁺ to Na ⁺ 80 – 120 | Recovery of metals from aqueous and non-aqueous streams. |

*meq/dry g

SAC: Strong Acid Cation, SBA: Strong Base Anion, WBA: Weak Base Anion, WAC: Weak Acid Cation, SPL: Speciality

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications | |
|-------------------------------------|--------------------|----------------------|--------------------------|--|-----------------------------------|--------------------|----------------------------------|--------------------------------|------------------------|--|---|
| Chemical Process Application | | | | | | | | | | | |
| Anion Exchange Resins | | | | | | | | | | | |
| SBA | Gel | GS 300 (OH) (Type I) | Styrene DVB | -N ⁺ R ₃ | OH | 0.3 – 1.2 | 60 – 70 | 60 (OH) | 1.0 | Cl ⁻ to OH ⁻ 25 – 30 | Removal and recovery from process streams. |
| | | 950 (Type I) | Cross linked Polyacrylic | -N ⁺ R ₃ | Cl ⁻ | 0.4 – 1.2 | 54 – 64 | 80 (Cl) | 1.2 | Cl ⁻ to OH ⁻ 25 – 30 | Removal of high level of colour bodies from sugar syrup. |
| | Macroporous | 830 S (Type 1) | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 57 – 66 | 80 (Cl ⁻) | 0.95 | Cl ⁻ to OH ⁻ 7 – 17 | Removal of colour bodies from sugar syrup and other process streams. This product conforms to NSF / ANSI / CAN 61 & is certified with GOLD SEAL from WQA. |
| | | 930 A (Type 1) | Crosslinked Polyacrylic | -N ⁺ R ₃ | Cl ⁻ | 0.3 – 1.2 | 65 – 72 | 80 (Cl ⁻) | 0.8 | Cl ⁻ to OH ⁻ 10 – 15 | Removal of high level of colour bodies from sugar syrup. |
| WBA | Macroporous | 845 (Type 1) | Styrene DVB | -N ⁺ R ₂ -N ⁺ R ₃ | - | 0.3 – 1.2 | 52 – 58 | 60 | 1.1 | Cl ⁻ to OH ⁻ 20% | Treatment of non-aqueous solution such as deashing of glucose, dextrose, sorbitol, gelatin & purification of MSG. |
| | | 860 S | Styrene DVB | -N ⁺ R ₂ -N ⁺ R ₃ | Free base | 0.3 – 1.2 | 50 – 58 (Cl ⁻) | 60 | 1.3 | FB to hydrochloride 25 max | Treatment of non-aqueous solution such as deashing of glucose, dextrose, sorbitol, gelatin & purification of MSG. |
| | | 870 | Styrene DVB | -N ⁺ R ₂ | Free base | 0.3 – 1.2 | 52 – 62 | 60 | 1.6 | FB to hydrochloride 25 max | Deacidification of process streams. |
| | | 880 | Styrene DVB | -N ⁺ R ₂ -N ⁺ R ₃ | Free base | 0.3 – 1.2 | 58 – 63 | 60 | 1.2 | FB to hydrochloride 25 max | Colour removal from textile effluent. |
| | | 890 | Styrene DVB | -N ⁺ R ₂ -N ⁺ R ₃ | Free base | 0.3 – 1.2 | 52 – 56 | 60 | 1.4 | - | Removal of strong acids in non water, pharma & speciality applications. |
| Cation Exchange Resins | | | | | | | | | | | |
| SAC | Macroporous | 790 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.3 – 1.2 | 51 – 55 | 120 | 1.9 (Na ⁺) | Na ⁺ to H ⁺ 2 – 6 | Special grade cation exchanger for applications demanding higher oxidation stability such as gelatin purification, heavy metal removal etc. |
| WAC | Macroporous | 652 | Methacrylic acid DVB | COO ⁻ | H ⁺ | 0.3 – 1.2 | 47 – 55 | 100 | 3.5 | H ⁺ to Na ⁺ 75 min | Ideal for the uptake of toxic / undesirable heavy metals, temporary hardness from process liquor and industrial water. |
| | Gel | 236 P | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | 0.3 – 1.2 | 46 – 54 | 120 | 4 | H ⁺ to Na ⁺ 80 – 120 | Removal of alkaline hardness from water in Beverage Industry. |
| Mixed Bed Resin | | | | | | | | | | | |
| | | GMW 11 (GVI) | Crosslinked Polystyrene | -SO ₃ ⁻ -N ⁺ R ₂ | H ⁺ OH ⁻ | 0.3 – 1.2 | - | 60 | - | - | Specially developed mix of resins for use in electroplating applications. Colour changes at the time of exhaustion. |

* meq/dry g

SAC: Strong Acid Cation, SBA: Strong Base Anion, WBA: Weak Base Anion, WAC: Weak Acid Cation, SPL : Speciality

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications |
|---|--------------------|-----------------------------|--------------------------------|---------------------|----------------------------|--------------------|----------------------------------|--------------------------------|-----------------------|---|
| Pharmaceutical Grade Resins | | | | | | | | | | |
| Active Pharmaceutical Ingredients (API's) | 254 | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | < 0.15 | ≤10 | - | - | - | Sustained release agent in drug formulations. |
| | 404 | Styrene DVB | -SO ₃ ⁻ | Ca ⁺⁺ | < 0.15 | ≤8 | - | - | - | Treatment of Hyperkalaemia. |
| | 454 | Styrene DVB | -N ⁺ R ₃ | Cl ⁻ | >0.075 – 45% <0.15 – 1% | ≤12 | - | 1.8 – 2.2** | - | Cholestyramine resin – used for lowering serum cholesterol levels. Taste masking, drug stabilisation, controlled release & active ingredient. |
| Speciality Excipient Resins | 204 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | < 0.15 | ≤5 | - | 10.0* | - | Taste masking of bitter drugs such as Norfloxacin, Ofloxacin, Roxithromycin, Dicyclomine Hydrochloride, Famotidine and B ₁₂ stabilisation etc. |
| | 214 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | < 0.15 | ≤5 | - | 10.0* | - | Taste masking of bitter drugs such as Azithromycin |
| | 234 | Crosslinked Polyacrylic | -COO ⁻ | K ⁺ | < 0.15 | ≤10 | - | - | - | Taste masking of bitter drugs such as Ciprofloxacin, Chloroquine Phosphate etc. as well as tablet disintegration. |
| | 254 | Styrene DVB | -SO ₃ ⁻ | Na ⁺ | < 0.15 | ≤10 | - | - | - | Sustained release agent in drug formulations. |
| | 264 | Crosslinked Polyacrylic | -COO ⁻ | H ⁺ | < 0.15 | ≤5 | - | 10.0* | - | Stabilisation of Vitamin B ₁₂ |
| | 294 | Crosslinked Polymethacrylic | -COO ⁻ | K ⁺ | < 0.15 | ≤10 | - | - | - | Tablet disintegrant/taste masking. Product meets specifications of Polacrillin Potassium, USP. |
| | 464 | Crosslinked Polymethacrylic | -COO ⁻ | H ⁺ | < 0.15 | ≤5 | - | 10* | - | Nicotine taste masking and sustained release. |

* meq/dry g

** sodium glycocholate exchange capacity

INDION® Ion Exchange Resins

Properties and Applications - Summarised Data

| Resin Type | INDION Designation | Matrix Type | Functional Group | Standard Ionic Form | Particle Size mm | Moisture Content % | Maximum Operating Temperature °C | Total Exchange Capacity meq/ml | Reversible Swelling % | Applications |
|---|--------------------|-------------|--------------------------------|---------------------|------------------|--------------------|----------------------------------|--------------------------------|-----------------------|--|
| Adsorbent Grade Resins | | | | | | | | | | |
| SPL | PA 500 | Styrene DVB | - | - | 0.3 – 1.2 | 63 – 67 | 150 | - | - | Purification of Aloe Vera juice and Methi extract. |
| | PA 600 | Styrene DVB | - | - | 0.3 – 1.2 | 55 – 65 | 130 | - | - | High surface area polymers for recovering non-polar substances from aqueous and non aqueous streams. |
| | PA 800 | Styrene DVB | - | - | 0.3 – 1.2 | 54 – 60 | 150 | - | - | Phenol removal from HCl and effluent. |
| | PA 1200 | Styrene DVB | - | - | 0.4 – 1.2 | 52 – 62 | 120 | - | - | High surface area polymers for recovering non-polar substances from aqueous and non aqueous streams. |
| Biodiesel Manufacture & Purification | | | | | | | | | | |
| SPL | 190 | Styrene DVB | -SO ₃ ⁻ | H ⁺ | 0.42 – 1.2 | <3 | 150 | 4.7* | - | Esterification of FFA. |
| | BF 100 | Styrene DVB | -N ⁺ R ₃ | OH ⁻ | 0.3 – 1.2 | 63 – 75 | - | 0.9 | - | Purification of raw bio-diesel to remove residual FFA from 0.5 - 1.0% to less than 0.1%. |
| | BF 170 | Styrene DVB | Acidic | - | 0.3 – 1.2 | ≤3 | - | - | - | Purification of raw bio-diesel for removal of glycerine, soap, moisture etc. |

* meq/dry g

SPL : Speciality

For more information visit us at : www.ionresins.com

We offer several other speciality resins for a wide variety of applications. These include fine mesh resins for chromatographic separations; dessicant grade resins for moisture removal from solvents & resins for peptide synthesis.

*meq/dry g